



## **Lead Sheet Sealant**

Revision: 05/10/2022 Page 1 from 2

#### **Technical data**

| Basis                              | Polysiloxane   |
|------------------------------------|--|
| Consistency                        | Stable paste   |
| Curing system                      | Moisture curing                                      |
| Skin formation* (23°C/50% R.H.)    | Ca. 6 min  |
| Curing speed * (23°C/50% R.H.)     | Ca. 2 mm/24h   |
| Hardness**                         | Ca. 25 ± 5 Shore A                                   |
| Density                            | Ca. 1,00 g/ml (transp) Ca. 1,22 g/ml (colors)        |
| Elastic recovery (ISO 7389)**      | > 80 %   |
| Maximum allowed distortion         | 20 %   |
| Max. tension (ISO 37)**            | Ca. 1.05 N/mm <sup>2</sup>                           |
| Elasticity modulus 100% (ISO 37)** | Ca. 0.30 N/mm²                                       |
| Elongation at break (ISO 37)**     | Ca. 700 %  |
| Temperature resistance**           | -60 °C → 120 °C                                      |
| Application temperature            | $5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$ |

<sup>\*</sup> These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## **Product description**

Lead Sheet Sealant is a high quality, elastic, 1-component sealant based on silicones.

#### **Properties**

- Very easy to apply
- Permanently elastic after curing
- Very good adhesion on many materials
- UV-resistant
- Very good resistance to ageing
- MEKO free
- · Not suitable for natural stone
- Not paintable

## **Applications**

- Sealing lead flashing into brick, stone or concrete.
- Joints on gutters, downpipes and venting.

## **Packaging**

Colour: grey

Packaging: 290 ml cartridge

### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

#### **Substrates**

Substrates: all usual building substrates Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be primed with Primer 150. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). We recommend a preliminary adhesion and compatibility test on every surface. Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass.

#### Joint dimensions

Min. width for joints: 5 mm Max. width for joints: 30 mm Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width =  $2 \times 10^{-5}$  joint depth. Three-point adhesion should be avoided at all time. Too small joint dimensions can have the effect that the silicone is pulled off because of too large movements.

## Application method

Apply the product by means of a manual-, battery- or pneumatic- caulking gun. Apply Lead Sheet Sealant evenly without air

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudal (UK) Limited Unit 1, Centurion Way
Tel: +44 1827-261.092 Fax: +44 1827-284.454





# **Lead Sheet Sealant**

Revision: 05/10/2022 Page 2 from 2

inclusions into the joint. Smoothen the joint with a spatula with the help of finishing solution. Avoid that soapy solution comes between the joint edges and sealant (to prevent adhesion loss).

Application method: With a manual, pneumatic or accu caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material.

### **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

#### **Remarks**

- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA or Silirub+ S8800 for this application.
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Because of the diversity we recommend to do adhesion tests on aluminum lackers, textured coating and PVC before application.
- In an acid environment or in a dark room, a sealant can slightly turn yellow. Under the influence of sunlight it can turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution.
   This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- Do not use in applications where continuous water immersion is possible.
- Do not use on polycarbonate. Use Silirub PC instead.

- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Contact with bitumen, tar or other
  plasticizer releasing materials such as
  EPDM, neoprene, butyl, etc. is to be
  avoided since it can give rise to
  discolouration and loss of adhesion.

#### **Environmental clauses**

Leed regulation:

Lead Sheet Sealant conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

#### Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudal (UK) Limited Unit 1, Centurion Way UK-Tamworth B77 5PN Tel: +44 1827-261.092 Fax: +44 1827-284.454 www.soudal.com